

11-06-00

A

Attorney Docket: Breyné 9

11/03/00



ASSISTANT COMMISSIONER FOR PATENTS
Washington, DC 20231

Sir:

Transmitted herewith for filing is the patent application of:

Inventor(s): **Olivier BREYNE, You-Ping CHAN and Patrick JEAN**

Title: **Naphthopyrans With A Heterocycle In The 5, 6-Position, Preparation, And (Co)Polymer Compositions And Matrices Containing Them**

Enclosed are:

- ☐ Assignment and Assignment Transmittal
☐ _____ sheet(s) of drawings
☒ Unexecuted Declaration in Original Application
☐ Information Disclosure Statement/Form PTO-1449
☐ A certified copy of French Application No. 99 13791, filed November 4, 1999 the priority of which is claimed.

The filing fee has been calculated as shown below:

CLAIMS AS FILED

	No. Filed	No. Extra	Rate	Basic Fee
				\$710.00
Total Claims	37	- 20 =	17	x \$18.00 \$ 306.00
Independent Claims	1	- 3 =	0	x \$80.00 \$
Multiple Claims				+ \$270.0 \$

TOTAL: \$1016.00

- ☒ Authorization is given by Corning Incorporated to charge **Deposit Account No. 03-3325**. A triplicate copy of this sheet is enclosed.
- ☒ The Commissioner is hereby authorized by Corning Incorporated to charge payment of the following fees associated with this communication or credit any overpayment to **Deposit Account No. 03-3325**. A triplicate copy of this sheet is enclosed.

- ☒ Any additional filing fees required under 37 CFR 1.16.
☒ Any patent application processing fees under 37 CFR 1.17.
☒ Any assignment recording fee under 37 CFR 1.21(h).

Respectfully submitted,

Angela N. Nwagwu
 Angela N. Nwagwu
 Registration No. 34,229
 Corning Incorporated
 SP-TI-3
 Corning, NY 14831
 (607) 974-3455

Date: Nov. 2, 2000

I hereby certify that this paper is being deposited with the United States Postal Service "Express Mail Post Office to Addressee" service under 37 CFR 1.10 on the date indicated above and is Addressed to the Commissioner of Patents and Trademarks, Washington, DC 20231

Signature

Colleen E Doherty

Date of Signature:

November 3, 2000

Express Mail No. EL689105173US



NAPHTHOPYRANS WITH A HETEROCYCLE IN THE 5, 6-POSITION,
PREPARATION, AND (CO)POLYMER COMPOSITONS AND
MATRICES CONTAINING THEM

This application claims the benefit of priority of FR Application No. 99 13791, filed November 4, 1999, entitled Naphthopyrans With A Heterocycle In The 5, 6-Position, Preparation, And (Co)Polymer Compositons And Matrices Containing Them, of Breyne et al.

The present invention relates to novel compounds of the fused naphthopyran type which have photochromic properties in particular. It further relates to the photochromic compositions and photochromic ophthalmic articles (for example lenses) containing said naphthopyrans. The invention further encompasses the preparation of these novel compounds.

Photochromic compounds are capable of changing color under the influence of a poly- or monochromatic light (for example UV) and of returning to their initial color when the light irradiation ceases or under the influence of temperature and/or a different poly- or monochromatic light from the first.

Photochromic compounds are applicable in various fields, for example for the manufacture of ophthalmic lenses, contact lenses, sunglasses, filters, optics for movie cameras, ordinary cameras or other optical and observational devices, glass panes, decorative objects or display elements, or for the storage of data by optical recording (coding).

In the field of ophthalmic optics and particularly spectacles, a photochromic lens, comprising one or more photochromic compounds, must have:


- a high transmission in the absence of ultraviolet,
- a low transmission (high colorability) under solar irradiation,
- appropriate coloration and decolorization kinetics,
- a tint acceptable to the consumer (preferably gray or brown), preferably with maintenance of the chosen tint during the coloration and decolorization of the lens,
- maintenance of the performance characteristics and the properties over the temperature range 0-40°C, and
- a substantial durability because the intended objectives are sophisticated and hence expensive corrective lenses.

These lens characteristics are in fact determined by the active photochromic compounds which the lens contains, it also being necessary for said compounds to


be perfectly compatible with the organic, mineral or even hybrid substrate of which the lens is made.

It should furthermore be noted that, to obtain a gray or brown tint, it may be necessary to use at least two photochromic substances of different colors, i.e. having different maximum absorption wavelengths in the visible. This association makes yet more demands on the photochromic compounds. In particular, the coloration and decolorization kinetics of the (two or more) associated active photochromic compounds must be substantially identical. The same applies to their stability over time and also to their compatibility with a plastic or mineral substrate.

The benzopyrans or naphthopyrans described in the following patents or patent applications may be mentioned among the numerous photochromic compounds described in the prior art: US-A-3 567 605, US-A-3 627 690, US-A-4 826 977, US-A-5 200 116, US-A-5 238 981, US-A-5 411 679, US-A-5 429 744, US-A-5 451 344, US-A-5 458 814, US-A-5 651 923, US-A-5 645 767, US-A-5 698 141, US-A-5 783 116, WO-A-95 05382, FR-A-2 718 447, WO-A-96 14596 and WO-A-97 21698, said compounds having the reduced formulae below:




Benzopyrans




Naphthopyrans

Patent US-A-5 783 116 more specifically describes naphthopyrans of the following general structure:



Patent US-A-5 811 034 claims the following general structure in particular:





US-A-5 811 034

5 These compounds are said to satisfy the specifications defined above. In reality, although these compounds do indeed have one or more of the desired basic properties, such as a high transmission in the absence of ultraviolet and a high colorability under solar irradiation, none of the compounds described hitherto have the complete combination of desired properties which is necessary for the
10 production of satisfactory articles. In particular, none of these compounds is intrinsically gray or brown and there is still a need to use a complementary photochromic substance in order to obtain one of these two tints.

 In this context, it is to the inventors' credit that they took an interest in this type of derivative as a basis for the development of novel photochromic
15 substances, and that they are proposing a novel family of molecules possessing particularly advantageous photochromic properties.

 Thus, according to a first feature, the present invention relates to compounds of formula (I) or (II):



in which:

- X is an oxygen or NR₆, R₆ being a hydrogen, a linear or branched alkyl group containing from 1 to 12 carbon atoms, a cycloalkyl group containing from 3 to 12 carbon atoms or an aryl or heteroaryl group containing in its basic structure 6 to 24 carbon atoms or, respectively, 4 to 24 carbon atoms and at least one heteroatom selected from sulfur, oxygen and nitrogen, said basic structure optionally being substituted by at least one substituent selected from a linear or branched alkyl containing 1 to 12 carbon atoms, a linear or branched alkoxy containing 1 to 12 carbon atoms, a halogen and a hydroxy;
- R₄ and R₅, which are identical or different, independently are a hydrogen, a hydroxy or a linear or branched alkyl group containing 1 to 6 carbon atoms, or together form an oxo group (=O);
- R₁ and R₂, which are identical or different, independently are:
 - hydrogen,
 - a linear or branched alkyl group containing from 1 to 12 carbon atoms,
 - a cycloalkyl group containing from 3 to 12 carbon atoms,
 - an aryl or heteroaryl group containing in its basic structure 6 to 24 carbon atoms or, respectively, 4 to 24 carbon atoms and at least one heteroatom selected from sulfur, oxygen and nitrogen, said basic structure optionally being substituted by at least one substituent selected from the group of substituents given below:
 - + a halogen, especially fluorine, chlorine or bromine,
 - + a hydroxy,
 - + a linear or branched alkyl group containing from 1 to 12 carbon atoms,
 - + a linear or branched alkoxy group containing from 1 to 12 carbon atoms,
 - + a haloalkyl or haloalkoxy group corresponding respectively to the above

(C₁-C₁₂)alkyl or (C₁-C₁₂)alkoxy groups substituted by at least one halogen atom, especially a fluoroalkyl group of this type,


- + a phenoxy or naphthoxy group optionally substituted by at least one linear or branched alkyl or alkoxy group containing from 1 to 12 carbon atoms,
- + a linear or branched alkenyl group containing from 2 to 12 carbon atoms, especially the vinyl group or the allyl group,
- + a group -NH₂,
- + a group -NHR, R being a linear or branched alkyl group containing from 1 to 6 carbon atoms or a phenyl optionally substituted by at least one linear or branched alkyl containing from 1 to 6 carbon atoms,
- + a group :



R' and R'', which are identical or different, independently being a linear or branched alkyl group containing from 1 to 6 carbon atoms or a phenyl optionally substituted by at least one linear or branched alkyl containing 1 to 6 carbon atoms, or, together with the nitrogen atom to which they are bonded, being a 5- to 7-membered ring which can contain at least one other heteroatom selected from oxygen, sulfur and nitrogen, said nitrogen optionally being substituted by a group R''', which is a linear or branched alkyl group containing from 1 to 6 carbon atoms, or

- + a methacryloyl group or an acryloyl group,
- an aralkyl or heteroaralkyl group in which the alkyl group is linear or branched and contains from 1 to 4 carbon atoms and in which the aryl or heteroaryl moiety is as defined above for the aryl or heteroaryl group, or said two substituents R₁ and R₂ together form an adamantyl, norbornyl, fluorenylidene, di(C₁-C₆)alkylanthracenyliidene or spiro(C₅-C₆)cycloalkylanthracenyliidene group, said group optionally being substituted by at least one of the substituents listed above for R₁ and R₂ as an aryl or heteroaryl group;
- R₃, which are identical or different, independently are:
 - a halogen, especially fluorine, chlorine or bromine,

- a hydroxy,
- a linear or branched alkyl group containing from 1 to 12 carbon atoms (advantageously from 1 to 6 carbon atoms),
- a cycloalkyl group containing from 3 to 12 carbon atoms,
- 5 - a linear or branched alkoxy group containing from 1 to 12 carbon atoms (advantageously from 1 to 6 carbon atoms),
- a haloalkyl, halocycloalkyl or haloalkoxy group corresponding respectively to the above alkyl, cycloalkyl and alkoxy groups substituted by at least one halogen atom selected especially from fluorine, chlorine and bromine,
- 10 - an aryl or heteroaryl group as defined above for R₁ and R₂,
- an aralkyl or heteroaralkyl group, the alkyl group, which is linear or branched, containing from 1 to 4 carbon atoms and the aryl and heteroaryl groups being as defined above for R₁ and R₂,
- a phenoxy or naphthoxy group optionally substituted by at least one linear or branched alkyl or alkoxy group containing from 1 to 12 carbon atoms,
- 15 - one of the following amine or amide groups: -NH₂, -NHR, -CONH₂, -CONHR,



- R, R' and R'' respectively being as defined above for the amino substituents of R₁ and R₂ as aryl or heteroaryl, or
- 20 - a group -OCOR₇ or -COOR₇, R₇ being a linear or branched alkyl group containing from 1 to 6 carbon atoms, a cycloalkyl group containing from 3 to 6 carbon atoms or a phenyl group, optionally substituted by at least one of the substituents listed above for R₁ and R₂ as aryl or heteroaryl, or
 - 25 at least two adjacent groups R₃ together form an aromatic or non-aromatic cyclic group with one ring or two fused rings, which can contain at least one heteroatom selected from the group comprising oxygen, sulfur and nitrogen, it being possible for said ring(s), which are independently aromatic or non-aromatic and 5- to 7-membered, to contain at least one substituent selected
 - 30 from a group as defined above by way of substituents of the basic structure of the aryl or heteroaryl group representing R₁ or R₂; and
 - m is an integer from 0 to 4.

Those skilled in the art will obviously have understood that the branched

alkyl, alkoxy and alkenyl groups as defined above contain a sufficient number of carbons to be able to be branched (respectively more than 3, more than 3 and more than 4 carbon atoms).

- 5 The compounds of the invention - naphthopyrans of formula (I) or (II) - possess a high colorability associated with decolorization kinetics appropriate to the intended applications. The colors, which are readily accessible, vary from orange to violet.

Among said compounds of formula (I) or (II) of the invention, there are those in which:

- 10 • X is an oxygen. Among these compounds, the following two subfamilies are very particularly preferred: the subfamily of compounds of formula (I) or (II) in which X = O, as stated, and R₄ and R₅ together form an oxo group, and the subfamily of compounds of formula (I) or (II) in which X = O, as stated, and R₄ and R₅ are hydrogens; and those in which:
- 15 • X is a group NR₆. Among these compounds, the following three subfamilies are very particularly preferred: the subfamily of compounds of formula (I) or (II) in which X = NR₆, as stated, and R₄ and R₅ together form an oxo group, the subfamily of compounds of formula (I) or (II) in which X = NR₆, as stated, and R₄ and R₅ are hydrogens, and the subfamily of compounds of formula (I) or (II) in which X = NR₆, as stated, R₄ is a hydrogen and R₅ is a hydroxy.
- 20

With reference to the substituents R₁ and R₂, the preferred compounds of formula (I) or (II) are those in which :


- 25 • R₁ and R₂ are identical or different and independently are optionally substituted aryl or heteroaryl groups whose basic structure is selected from the group comprising phenyl, naphthyl, biphenyl, pyridyl, furyl, benzofuryl, dibenzofuryl, N-(C₁-C₆)alkylcarbazole, thienyl, benzothieryl, dibenzothieryl and julolidinyl groups, R₁ and/or R₂ advantageously being a para-substituted phenyl group; or those in which :

- 30 • R₁ and R₂ together form an adamantyl or norbornyl group.
- In a first embodiment of the invention, the compounds (I) or (II) are such that at least two of their adjacent substituents R₃ do not together form a ring.

- In a second embodiment of the invention, the compounds (I) and (II) are such that they comprise at least two adjacent groups R₃ which together form an aromatic or non-aromatic cyclic group with one ring or two fused rings, which can contain at least one heteroatom selected from the group comprising oxygen, sulfur
- 35

and nitrogen, it being possible for said ring(s), which independently are aromatic or non-aromatic and 5- to 7-membered, to contain at least one substituent selected from a group as defined above by way of substituents of the basic structure of the aryl or heteroaryl group representing R_1 or R_2 .

- 5 The compounds of the invention can be synthesized according to the following general scheme :



- 10 R_1 , R_2 , R_3 , R_6 and m being as defined above with reference to formulae (I) and (II).

The starting materials A can be obtained by a procedure described by Kotsuki et al. (Bull. Chem. Soc. Jpn. 1994, 67, 599).

The intermediates B are obtained by processes well known to those skilled in the art (cf. e.g. EP-A-0 562 915 and US-A-5 783 116).

- 15 The compounds C according to the invention are obtained by saponification of the esters in a basic medium, followed by a thermal cyclization-dehydration.

The compounds D according to the invention are obtained by condensing compounds C with a primary amine.

- 20 The other compounds of the invention in which R_4 and/or R_5 = H or OH are obtained by reducing compounds C or D. Controlled reduction of the anhydrides (compounds C) with hydrides, such as NaBH_4 or LiAlH_4 , yields lactones (R_4 and R_5 = H) and/or hydroxyactones (R_4 = H and R_5 = OH) and controlled reduction of

the imides yields lactams (R_4 and $R_5 = H$) or hydroxyactams ($R_4 = H$ and $R_5 = OH$) (cf. e.g. the following references: Bailey and Johnson, J. Org. Chem. 1970, 35, 3574 and Sato et al., Bull. Chem. Soc. Jpn. 1988, 61, 2238). Likewise, the anhydride or the imide is reacted with one or two equivalents of an organo-magnesium compound (alkylMgBr) to give the derivatives in which $R_4 = OH$ and $R_5 = \text{alkyl}$ or $R_4 = R_5 = \text{alkyl}$ (cf. e.g. Zhang et al., J. Amer. Chem. Soc. 1993, 115, 3670-3673). The compounds in which $R_4 = H$ and $R_5 = \text{alkyl}$ ($X = O$ or NR_6) can be synthesized according to the chemistry described by Canonne et al. in Tetrahedron 1988, 44, 2903.

According to a third feature, the invention relates to (co)polymers and/or crosslinked products obtained by the polymerization and/or crosslinking and/or grafting of at least one compound (I) or (II) as defined above. The compounds (I) or (II) according to the invention can be (co)monomers *per se* and/or can be included in (co)polymerizable and/or crosslinkable (co)monomers. The (co)polymers and/or crosslinked products obtained in this way can constitute photochromic matrices such as those presented below.

According to a fourth feature, the present invention relates to the use of said compounds of formula (I) or (II) of the invention as photochromic agents. The invention therefore further relates:

- on the one hand to novel photochromic compounds which consist of the naphthopyran derivatives as defined above, taken in isolation or in a mixture with one another and/or with at least one other photochromic compound of a different type and/or with at least one non-photochromic coloring agent; and
- on the other hand to novel photochromic compositions which comprise at least one compound (I) or (II), as defined above, and/or at least one linear or crosslinked (co)polymer containing in its structure at least one compound (I) or (II) according to the invention. Such photochromic compositions can contain at least one other photochromic compound of a different type and/or at least one non-photochromic coloring agent and/or at least one stabilizer. These photochromic compounds of a different type, non-photochromic coloring agents and stabilizers are products of the prior art known to those skilled in the art.

Associations of photochromic compounds of the invention and/or associations of photochromic compounds of the invention and photochromic compounds of a different type, according to the prior art, are particularly

09706122.110300

recommended within the framework of the present invention, such associations being of value in that they are suitable for generating the gray or brown tints sought after by the public in applications such as ophthalmic lenses or sunglasses. These complementary photochromic compounds can be the ones known to those skilled in the art and described in the literature, for example chromenes (US-A-3 567 605, US-A-5 238 981, WO-A-94 22850, EP-A-0 562 915), spiropyrans or naphtho-spiropyrans (US-A-5 238 981) and spiroxazines (CRANO et al., "*Applied Photochromic Polymer Systems*", published by Blackie & Son Ltd, 1992, chapter 2).

Said compositions according to the invention can also contain:

- 10 - non-photochromic coloring agents for adjusting the tint,
- and/or one or more stabilizers, for example an antioxidant,
- and/or one or more UV inhibitors,
- and/or one or more free radical inhibitors,
- and/or one or more deactivators of photochemical excited states.
- 15 These additives can make it possible in particular to improve the durability of said compositions.

The compounds of the invention, envisaged within the framework of their photochromic applications, can be used in solution. Thus a photochromic solution can be obtained by solubilizing at least one of said compounds in an organic solvent such as toluene, dichloromethane, tetrahydrofuran or ethanol. The solutions obtained are generally colorless and transparent. They develop a strong coloration when exposed to sunlight and return to the colorless state when placed in a zone of lower exposure to solar radiation or, in other words, when they are no longer subjected to UV. A very low concentration of product (of the order of 0.01 to 5% by weight) is generally sufficient to obtain an intense coloration.

Furthermore, the compounds according to the invention are compatible with substrate matrices made of organic polymer or mineral (even hybrid) material, either included in said matrices or coated on said matrices.

Therefore, within the framework of the fourth feature of the invention pertaining to photochromic applications, the invention relates to a matrix containing:

- at least one compound (I) or (II) as defined above,
- and/or at least one (co)polymer and/or crosslinked product as defined above,
- and/or at least one composition as presented above.

In fact, the most advantageous applications of the compounds of the


invention are those in which the photochromic substance is uniformly dispersed within or over the surface of a matrix formed by a polymer and/or a copolymer and/or a mixture of (co)polymers.

5 Mirroring their behavior in solution, the compounds (I) or (II) included in a polymer matrix are colorless or slightly colored in the initial state and rapidly develop an intense coloration under UV light (365 nm) or a light source of the solar type. Finally, they return to their initial color when the irradiation ceases.

10 The processes which can be envisaged for obtaining such a matrix are very varied. An example which may be mentioned among the processes known to those skilled in the art is diffusion of the photochromic substance into the (co)polymer from a suspension or solution in a silicone oil, an aliphatic or aromatic hydrocarbon or a glycol, or from another polymer matrix. The diffusion is commonly carried out at a temperature of 50 to 200°C for a period of 15 minutes to a few hours, depending on the nature of the polymer matrix. Another practical
15 technique consists in mixing the photochromic substance into a formulation of polymerizable substances, depositing this mixture on a surface or in a mold and then performing the copolymerization. These and other practical techniques are described in the article by CRANO et al. entitled "*Spiroxazines and their use in photochromic lenses*" in Applied Photochromic Polymer Systems, published by
20 Blackie & Son Ltd - 1992.

The following products may be mentioned as examples of preferred polymer materials for forming matrices which can be used in optical applications of the photochromic compounds according to the invention:

- alkyl, cycloalkyl, (poly or oligo)ethylene glycol, aryl or arylalkyl mono-, di-,
25 tri- or tetraacrylate or mono-, di-, tri- or tetramethacrylate which is optionally halogenated or contains at least one ether and/or ester and/or carbonate and/or carbamate and/or thiocarbamate and/or urea and/or amide group,
- polystyrene, polyether, polyester, polycarbonate (e.g. polybisphenol-A carbonate, polydiallyldiethylene glycol carbonate), polycarbamate,
30 polyepoxide, polyurea, polyurethane, polythiourethane, polysiloxane, polyacrylonitrile, polyamide, aliphatic or aromatic polyester, vinylic polymers, cellulose acetate, cellulose triacetate, cellulose acetate-propionate or polyvinylbutyral,
- those obtained from difunctional monomers of the following formula:



in which:

- Δ R₁₀, R'₁₀, R₁₁ and R'₁₁ are identical or different and independently are a hydrogen or a methyl group,
- Δ m₁ and n₁ independently are integers between 0 and 4 inclusive and advantageously are independently equal to 1 or 2,
- Δ X and X', which are identical or different, are a halogen, preferably a chlorine and/or a bromine, and
- Δ p₁ and q₁ independently are integers between 0 and 4 inclusive, or
- copolymers of at least two types of copolymerizable monomers selected from the monomers which are precursors of the polymers listed above, preferably those belonging to the groups comprising (meth)acrylic, vinylic and allylic monomers and mixtures thereof.

Particularly preferably, the photochromic substances of the invention are used with resins which have a nanobiphase structure and are obtained by copolymerizing at least two specific, different difunctional monomers. Such resins have been described by the Applicant in patent application FR-A-2 762 845.

The amount of photochromic substance used in the (co)polymer matrix depends on the desired degree of darkening. The amount used is normally between 0.001 and 20% by weight.

Again according to the fourth feature pertaining to applications of the compounds (I) or (II) as photochromic substances, the present invention further relates to ophthalmic articles, such as ophthalmic lenses or sunglasses, comprising:

- at least one compound (I) or (II) according to the invention,
- and/or at least one (co)polymer and/or crosslinked product at least partially formed by at least one compound of the invention,
- and/or at least one photochromic composition as defined above,
- and/or at least one matrix (as defined above) made of an organic polymer, a mineral material or a mineral-organic hybrid material, said matrix optionally comprising initially at least one compound of the invention.

In practice, the articles to which the present invention relates more particularly are photochromic ophthalmic lenses or sunglasses, glass panes (windows for buildings, locomotive engines, automotive vehicles), optical devices,

decorative articles, articles for solar protection, data storage, etc.

The present invention is illustrated by the following Examples of the synthesis and photochromic validation of compounds of the invention. Said compounds of the invention are compared with compounds C1 and C2 of the prior art.


5

09705122.1.0000

EXAMPLES

EXAMPLE 1: SYNTHESIS OF THE COMPOUNDS (1.D) AND (1.E)

- 5 The compounds (1.D) and (1.E) were synthesized according to the following scheme:



10 Step 1:


- 3.6 g of the naphthol 1.A (obtained by the process described by Kotsuki et al., Bull. Chem. Soc. Jpn. 1994, 67, 599) are reacted with 4.8 g of bis-1,1-(paramethoxyphenyl)propyn-1-ol in refluxing toluene for 4 hours in the presence of a catalytic amount of bromoacetic acid. After purification by chromatography on a silica column, 3 g of the intermediate 1.B are isolated.

Step 2:

- The product 1.B is refluxed in ethanol in the presence of excess sodium hydroxide. The product is then isolated by acidification and extraction with toluene. The toluene solution is then refluxed for 6 hours with azeotropic distillation of water. After evaporation of the solvent and crystallization, 1.2 g of the compound (1.C) are isolated. Its structure is confirmed by proton NMR.

Step 3:

- 0.5 g of the compound (1.C) is solubilized in a THF/methanol mixture and then reduced by the addition of excess NaBH_4 at room temperature. The product is then purified by chromatography on silica. 230 mg of a mixture consisting of 30% of 1.D and 70% of 1.E are isolated. Their structures are confirmed by proton NMR.

EXAMPLE 2: SYNTHESIS OF THE COMPOUNDS (2.E) AND (2.F)*Step 1:*

The derivative 2.C is synthesized as in Example 1 starting from 1-paramethoxyphenyl-1-phenylpropyn-1-ol.

Step 2:

- 0.65 g of the compound 2.C is reacted with 0.16 g of n-hexylamine in refluxing toluene for 2 hours. The reaction mixture is evaporated to dryness and the residue is refluxed again in 10 ml of xylene for 5 hours. After purification on a silica column, 0.75 g of the product 2.D is isolated.

Step 3:

- 0.75 g of the product 2.D is solubilized in a THF/methanol mixture (10 + 1 ml) and excess NaBH_4 is added in portions. After 20 minutes at room temperature, the product is purified by chromatography on silica. 50 mg of a

5

10

15

15

Said compounds are solubilized at a rate of 5 mg in 50 ml of THF and then the UV-visible absorptions are measured (optical path of 1 cm) before and after exposure to a 365 nm UV source. The tints and intensities developed are observed by placing the solutions in the sun or in a solar simulator. The properties of these compounds are given in the Table below.

COMPOUND	STRUCTURE	λ_{1}^{*}	$T_{1/2}^{**}$
1.D + 1.E (30 / 70 %)		500 nm	9 s
2E + 2F (50 / 50 %)		512 nm	20 s
C1		490 nm	39 s
C2		490 nm	89 s



* λ_1 = maximum of the longest wavelength band of the compound after exposure.

** $T_{1/2}$ = decolorization time corresponding to a 50% drop in absorption at $\lambda_{1\max}$.

- 5 Observation of the solutions in the presence of solar or UV radiation shows that the compounds of the invention have λ_1 values shifted towards longer wavelengths (bathochromic shift) and have more rapid decolorization kinetics. This observation is particularly obvious when comparing the λ_{\max} values of the compounds (1) with those of the analogous compounds C1 and C2.

WHAT IS CLAIMED IS:

1. A compound having the formula (I) or (II) below:



in which:

- X is an oxygen or NR₆, R₆ being a hydrogen, a linear or branched alkyl group comprising from 1 to 12 carbon atoms, a cycloalkyl group comprising from 3 to 12 carbon atoms, an aryl group comprising in its basic structure 6 to 24 carbon atoms, or a heteroaryl group comprising in its basic structure 4 to 24 carbon atoms and at least one heteroatom selected from sulfur, oxygen, and nitrogen, said aryl or heteroaryl group's basic structure optionally being substituted by at least one substituent selected from the group consisting of a linear or branched alkyl comprising 1 to 12 carbon atoms, a linear or branched alkoxy comprising 1 to 12 carbon atoms, a halogen, and a hydroxy;
- R₄ and R₅, which are identical or different, independently represent a hydrogen, a hydroxy, or a linear or branched alkyl group comprising 1 to 6 carbon atoms, or R₄ and R₅ together form an oxo group (=O);
- R₁ and R₂, which are identical or different, independently are:
 - hydrogen,
 - a linear or branched alkyl group comprising from 1 to 12 carbon atoms,
 - a cycloalkyl group comprising from 3 to 12 carbon atoms,
 - an aryl group comprising in its basic structure 6 to 24 carbon atoms or a heteroaryl group comprising in its basic structure 4 to 24 carbon atoms and at least one heteroatom selected from sulfur, oxygen, and nitrogen, said aryl or heteroaryl group's basic structure optionally being substituted with at least one substituent selected from the group consisting of:
 - + a halogen,

- + a hydroxy,
- + a linear or branched alkyl group comprising from 1 to 12 carbon atoms,
- + a linear or branched alkoxy group comprising from 1 to 12 carbon atoms,
- 5 + a haloalkyl or haloalkoxy group corresponding respectively to the above (C₁-C₁₂)alkyl or (C₁-C₁₂)alkoxy groups substituted with at least one halogen atom,
- + a phenoxy or naphthoxy group optionally substituted with at least one linear or branched alkyl or alkoxy group comprising from 1 to 12 carbon atoms,
- 10 + a linear or branched alkenyl group comprising from 2 to 12 carbon atoms,
- + an -NH₂ group,
- + an -NHR group, wherein R is a linear or branched alkyl group comprising from 1 to 6 carbon atoms or a phenyl group optionally substituted by at least one linear or branched alkyl comprising from 1 to 6 carbon atoms,
- 15 + a group having the formula:




wherein R' and R'', identical or different, independently represent a linear or branched alkyl group comprising from 1 to 6 carbon atoms or a phenyl group optionally substituted with at least one linear or branched alkyl comprising 1 to 6 carbon atoms, or R' and R'', together with the nitrogen atom to which they are bonded, represent a 5- to 7-membered ring which optionally comprises at least one other heteroatom selected from oxygen, sulfur, and nitrogen, said nitrogen optionally being substituted with a group R''', which is a linear or branched alkyl group comprising from 1 to 6 carbon atoms, and

- + a methacryloyl group or an acryloyl group, or
- an aralkyl or heteroaralkyl group in which the alkyl part is linear or branched and comprises from 1 to 4 carbon atoms and in which the aryl

or heteroaryl part is as defined above for the aryl or heteroaryl group,
or

said two substituents R_1 and R_2 together form an adamantyl, norbornyl,
fluorenylidene, di(C_1 - C_6)alkylanthracenyldiene, or spiro(C_5 - C_6)cycloalkyl-
anthracenyldiene group, said group being optionally substituted with at least
one of the substituents listed above for R_1 and R_2 as an aryl or heteroaryl group;

- R_3 , which are identical or different, independently are:
 - a halogen,
 - a hydroxy,
 - a linear or branched alkyl group comprising from 1 to 12 carbon atoms,
 - a cycloalkyl group comprising from 3 to 12 carbon atoms,
 - a linear or branched alkoxy group comprising from 1 to 12 carbon atoms,
 - a haloalkyl, halocycloalkyl, or haloalkoxy group corresponding respectively
to the above alkyl, cycloalkyl, and alkoxy groups substituted with at least
one halogen atom,
 - an aryl or heteroaryl group as defined above for R_1 and R_2 ,
 - an aralkyl or heteroaralkyl group in which the alkyl part is linear or
branched and comprises from 1 to 4 carbon atoms and in which the aryl or
heteroaryl part is as defined above for R_1 and R_2 ,
 - a phenoxy or naphthoxy group optionally substituted with at least one linear
or branched alkyl or alkoxy group comprising from 1 to 12 carbon atoms,
 - one of the following amine or amide groups: $-NH_2$, $-NHR$, $-CONH_2$,
 $-CONHR$,



R , R' , and R'' respectively being as defined above for the amino substituents
of R_1 and R_2 as aryl or heteroaryl, or

- a group $-OCOR_7$ or $-COOR_7$, wherein R_7 is a linear or branched alkyl group
comprising from 1 to 6 carbon atoms, a cycloalkyl group comprising from 3
to 6 carbon atoms, or a phenyl group optionally substituted with at least one
of the substituents listed above for R_1 and R_2 as aryl or heteroaryl,

or

at least two adjacent groups R_3 together form an aromatic or non-aromatic

cyclic group having one ring or two fused rings which ring(s) are 5- to 7-membered, which ring(s) optionally comprise at least one heteroatom selected from the group consisting of oxygen, sulfur, and nitrogen, and which ring(s) are optionally substituted with at least one substituent selected from those given above in the definition for the aryl or heteroaryl groups which can form R₁ or R₂; and

- m is an integer from 0 to 4.

2. A compound according to claim 1 having formula (I).

3. A compound according to claim 1 having formula (II).

4. A compound according to claim 1, wherein X is an oxygen.

5. A compound according to claim 1, wherein X is an oxygen and R₄ and R₅ together form an oxo group.

6. A compound according to claim 1, wherein X is an oxygen and each of R₄ and R₅ is a hydrogen.

7. A compound according to claim 1, wherein X is an NR₆ group.

8. A compound according to claim 1, wherein X is an NR₆ group and R₄ and R₅ together form an oxo group.

9. A compound according to claim 1, wherein X is an NR₆ group and each of R₄ and R₅ is a hydrogen.

10. A compound according to claim 1, wherein X is an NR₆ group, R₄ is a hydrogen, and R₅ is a hydroxy.

11. A compound according to claim 1, wherein

- R₁ and R₂ are identical or different and independently represent optionally substituted aryl or heteroaryl groups whose basic structure is selected from those of phenyl, naphthyl, biphenyl,

- pyridyl, furyl, benzofuryl, dibenzofuryl, N-(C₁-C₆)alkylcarbazole, thienyl, benzothienyl, dibenzothienyl, and julolidinyl groups; or
- R₁ and R₂ together form an adamantyl or norbornyl group.

5 12. A compound according to claim 11 having formula (I).

13. A compound according to claim 11 having formula (II).

14. A compound according to claim 11, wherein X is an oxygen.

10

15. A compound according to claim 11, wherein X is an NR₆ group.

16. A compound according to claim 1, wherein at least one of R₁ and R₂ is a para-substituted phenyl group.

17. A (co)polymer and/or crosslinked product obtained by polymerizing and/or crosslinking and/or grafting at least one monomer comprising at least one compound according to claim 1.

20

18. A photochromic compound which is constituted by a compound according to claim 1, or by a mixture of at least two compounds according to claim 1, or by a mixture of at least one compound according to claim 1 and at least one other photochromic compound of a different type and/or at least one non-photochromic coloring agent.

25

19. A photochromic composition which comprises:

- at least one compound according to claim 1, and/or
- at least one linear or crosslinked (co)polymer which contains, in its structure, at least one compound according to claim 1, and
- optionally, at least one other photochromic compound of a different type and/or at least one non-photochromic coloring agent and/or at least one stabilizer.

30


20. A (co)polymer matrix which comprises:

35

- at least one compound according to claim 1.

21. A (co)polymer matrix according to claim 20, wherein the (co)polymer is selected from the group consisting of:

- an alkyl, cycloalkyl, (poly or oligo)ethylene glycol, aryl or arylalkyl mono-, di-, tri-, or tetra- acrylate or mono-, di-, tri- or tetra- methacrylate which is optionally halogenated or which optionally comprises at least one ether and/or ester and/or carbonate and/or carbamate and/or thiocarbamate and/or urea and/or amide group,
- a polystyrene, polyether, polyester, polycarbonate, polycarbamate, polyepoxide, polyurea, polyurethane, polythiourethane, polysiloxane, polyacrylonitrile, polyamide, aliphatic or aromatic polyester, vinylic polymers, cellulose acetate, cellulose triacetate, cellulose acetate-propionate, or polyvinylbutyral,
- a (co)polymer obtained from a difunctional monomer of the following formula:



in which:

Δ R_{10} , R'_{10} , R_{11} and R'_{11} are identical or different and independently are a hydrogen or a methyl group,

Δ m_1 and n_1 independently are integers between 0 and 4 inclusive,

Δ X and X', which are identical or different, are a halogen, and

Δ p_1 and q_1 independently are integers between 0 and 4 inclusive;


- a copolymer of at least two types of copolymerizable monomers selected from the monomers which are precursors of the polymers listed above; and
- combinations thereof.

22. A (co)polymer matrix which comprises:

- at least one photochromic composition according to claim 19.

23. A (co)polymer matrix according to claim 22, wherein the (co)polymer is selected from the group consisting of:

- an alkyl, cycloalkyl, (poly or oligo)ethylene glycol, aryl or arylalkyl mono-, di-, tri-, or tetra- acrylate or mono-, di-, tri- or tetra- methacrylate which is optionally halogenated or which optionally comprises at least one ether and/or ester and/or carbonate and/or carbamate and/or thiocarbamate and/or urea and/or amide group,
- a polystyrene, polyether, polyester, polycarbonate, polycarbamate, polyepoxide, polyurea, polyurethane, polythiourethane, polysiloxane, polyacrylonitrile, polyamide, aliphatic or aromatic polyester, vinylic polymers, cellulose acetate, cellulose triacetate, cellulose acetate-propionate, or polyvinylbutyral,
- a (co)polymer obtained from a difunctional monomer of the following formula:



in which:

Δ R_{10} , R'_{10} , R_{11} and R'_{11} are identical or different and

independently are a hydrogen or a methyl group,

Δ m_1 and n_1 independently are integers between 0 and 4 inclusive,

Δ X and X', which are identical or different, are a halogen, and

Δ p_1 and q_1 independently are integers between 0 and 4 inclusive;

- a copolymer of at least two types of copolymerizable monomers selected from the monomers which are precursors of the

polymers listed above; and

- combinations thereof.

5

24. A (co)polymer matrix which comprises:

- at least one (co)polymer and/or crosslinked product according to claim 17.


10

25. A (co)polymer matrix according to claim 24, wherein the (co)polymer is selected from the group consisting of:

15

- an alkyl, cycloalkyl, (poly or oligo)ethylene glycol, aryl or arylalkyl mono-, di-, tri-, or tetra- acrylate or mono-, di-, tri- or tetra- methacrylate which is optionally halogenated or which optionally comprises at least one ether and/or ester and/or carbonate and/or carbamate and/or thiocarbamate and/or urea and/or amide group,
- a polystyrene, polyether, polyester, polycarbonate, polycarbamate, polyepoxide, polyurea, polyurethane, polythiourethane, polysiloxane, polyacrylonitrile, polyamide, aliphatic or aromatic polyester, vinylic polymers, cellulose acetate, cellulose triacetate, cellulose acetate-propionate, or polyvinylbutyral,
- a (co)polymer obtained from a difunctional monomer of the following formula:

25



in which:

30

- Δ R_{10} , R'_{10} , R_{11} and R'_{11} are identical or different and independently are a hydrogen or a methyl group,
- Δ m_1 and n_1 independently are integers between 0 and 4 inclusive,
- Δ X and X' , which are identical or different, are a halogen, and

Δ p_1 and q_1 independently are integers between 0 and 4 inclusive;

- a copolymer of at least two types of copolymerizable monomers selected from the monomers which are precursors of the polymers listed above; and
- combinations thereof.

26. An ophthalmic or solar article comprising:

- at least one compound according to claim 1.

27. An article according to claim 26, wherein said article is selected from the group consisting of a lens, a glass pane, or an optical device.

28. An ophthalmic or solar article comprising:

- at least one at least one photochromic composition according to claim 19.

29. An article according to claim 28, wherein said article is selected from the group consisting of a lens, a glass pane, or an optical device.

30. An ophthalmic or solar article comprising:

- at least one (co)polymer and/or crosslinked product according to claim 17.

31. An article according to claim 30, wherein said article is selected from the group consisting of a lens, a glass pane, or an optical device.

32. An ophthalmic or solar article comprising:

- at least one matrix according to claim 20.

33. An article according to claim 32, wherein said article is selected from the group consisting of a lens, a glass pane, or an optical device.

34. An ophthalmic or solar article comprising:

- at least one matrix according to claim 22.

35. An article according to claim 34, wherein said article is selected from the group consisting of a lens, a glass pane, or an optical device.

5

36. An ophthalmic or solar article comprising:

- at least one matrix according to claim 24.



37. An article according to claim 36, wherein said article is selected from the group consisting of a lens, a glass pane, or an optical device.

0
1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65
66
67
68
69
70
71
72
73
74
75
76
77
78
79
80
81
82
83
84
85
86
87
88
89
90
91
92
93
94
95
96
97
98
99
100
101
102
103
104
105
106
107
108
109
110
111
112
113
114
115
116
117
118
119
120
121
122
123
124
125
126
127
128
129
130
131
132
133
134
135
136
137
138
139
140
141
142
143
144
145
146
147
148
149
150
151
152
153
154
155
156
157
158
159
160
161
162
163
164
165
166
167
168
169
170
171
172
173
174
175
176
177
178
179
180
181
182
183
184
185
186
187
188
189
190
191
192
193
194
195
196
197
198
199
200
201
202
203
204
205
206
207
208
209
210
211
212
213
214
215
216
217
218
219
220
221
222
223
224
225
226
227
228
229
230
231
232
233
234
235
236
237
238
239
240
241
242
243
244
245
246
247
248
249
250
251
252
253
254
255
256
257
258
259
260
261
262
263
264
265
266
267
268
269
270
271
272
273
274
275
276
277
278
279
280
281
282
283
284
285
286
287
288
289
290
291
292
293
294
295
296
297
298
299
300
301
302
303
304
305
306
307
308
309
310
311
312
313
314
315
316
317
318
319
320
321
322
323
324
325
326
327
328
329
330
331
332
333
334
335
336
337
338
339
340
341
342
343
344
345
346
347
348
349
350
351
352
353
354
355
356
357
358
359
360
361
362
363
364
365
366
367
368
369
370
371
372
373
374
375
376
377
378
379
380
381
382
383
384
385
386
387
388
389
390
391
392
393
394
395
396
397
398
399
400
401
402
403
404
405
406
407
408
409
410
411
412
413
414
415
416
417
418
419
420
421
422
423
424
425
426
427
428
429
430
431
432
433
434
435
436
437
438
439
440
441
442
443
444
445
446
447
448
449
450
451
452
453
454
455
456
457
458
459
460
461
462
463
464
465
466
467
468
469
470
471
472
473
474
475
476
477
478
479
480
481
482
483
484
485
486
487
488
489
490
491
492
493
494
495
496
497
498
499
500
501
502
503
504
505
506
507
508
509
510
511
512
513
514
515
516
517
518
519
520
521
522
523
524
525
526
527
528
529
530
531
532
533
534
535
536
537
538
539
540
541
542
543
544
545
546
547
548
549
550
551
552
553
554
555
556
557
558
559
560
561
562
563
564
565
566
567
568
569
570
571
572
573
574
575
576
577
578
579
580
581
582
583
584
585
586
587
588
589
590
591
592
593
594
595
596
597
598
599
600
601
602
603
604
605
606
607
608
609
610
611
612
613
614
615
616
617
618
619
620
621
622
623
624
625
626
627
628
629
630
631
632
633
634
635
636
637
638
639
640
641
642
643
644
645
646
647
648
649
650
651
652
653
654
655
656
657
658
659
660
661
662
663
664
665
666
667
668
669
670
671
672
673
674
675
676
677
678
679
680
681
682
683
684
685
686
687
688
689
690
691
692
693
694
695
696
697
698
699
700
701
702
703
704
705
706
707
708
709
710
711
712
713
714
715
716
717
718
719
720
721
722
723
724
725
726
727
728
729
730
731
732
733
734
735
736
737
738
739
740
741
742
743
744
745
746
747
748
749
750
751
752
753
754
755
756
757
758
759
760
761
762
763
764
765
766
767
768
769
770
771
772
773
774
775
776
777
778
779
780
781
782
783
784
785
786
787
788
789
790
791
792
793
794
795
796
797
798
799
800
801
802
803
804
805
806
807
808
809
810
811
812
813
814
815
816
817
818
819
820
821
822
823
824
825
826
827
828
829
830
831
832
833
834
835
836
837
838
839
840
841
842
843
844
845
846
847
848
849
850
851
852
853
854
855
856
857
858
859
860
861
862
863
864
865
866
867
868
869
870
871
872
873
874
875
876
877
878
879
880
881
882
883
884
885
886
887
888
889
890
891
892
893
894
895
896
897
898
899
900
901
902
903
904
905
906
907
908
909
910
911
912
913
914
915
916
917
918
919
920
921
922
923
924
925
926
927
928
929
930
931
932
933
934
935
936
937
938
939
940
941
942
943
944
945
946
947
948
949
950
951
952
953
954
955
956
957
958
959
960
961
962
963
964
965
966
967
968
969
970
971
972
973
974
975
976
977
978
979
980
981
982
983
984
985
986
987
988
989
990
991
992
993
994
995
996
997
998
999
1000

ABSTRACT OF THE DISCLOSURE

The present invention relates to novel compounds of the naphthopyran type with a fused heterocycle in the 5,6-position. These compounds have formula (I) or

5 (II) given below:



These compounds (I) or (II) have valuable photochromic properties. The invention
 10 further relates to their preparation, to their applications as photochromic
 substances, and to the (co)polymer compositions and matrices containing them.

As a below named inventor, I declare that:

My residence, Post Office address and citizenship are as stated below next to my name.

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled **Naphthopyrans With A Heterocycle In The 5, 6-Position, Preparation, And (Co)Polymer Compositions And Matrices Containing Them.**

The specification of which (check only one item below):

- ☐ is attached hereto
- ☐ was filed as United States Application Serial No. _____ on _____
and was amended on _____ (if applicable)
- ☐ was filed as PCT international application number _____, on _____, and was
amended under PCT Article 19 on _____ (if applicable).

I hereby state that I have reviewed and understand the contents of the above-identified specification, including the claims, as amended by any amendment referred to above.

I acknowledge the duty to disclose information which is material to the examination of this application in accordance with Title 37, Code of Federal Regulations, § 1.56.

I hereby claim foreign priority benefits under Title 35, United States Code, § 119(a)-(d) or 365(b) of any foreign application(s) for patent or inventor's certificate or 365(a) of any PCT international application which designated at least one country other than the United States, listed below and have also identified below any foreign application for patent or inventor's certificate, on the same subject matter, having a filing date before that of the application on which priority is claimed:

- ☒ **Country:** France **Application No.:** 99 13791 **Filing Date:** November 4, 1999
- ☐ **NONE**

I hereby claim the benefit under Title 35 United States Code § 119(e) and § 120 of any United States application(s) or 365(c) of any PCT international application designating the United States listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States application in the manner provided by the first paragraph of Title 35 United States Code § 112, I acknowledge the duty to disclose material information as defined in Title 37 Code of Federal Regulations, § 1.56 which occurred between the filing date of the prior application and the national or PCT international filing date of this application:

- ☐ **Provisional No.:** _____ **Filed:** _____ **Status:** _____
- ☐ **Application No.:** _____ **Filed:** _____ **Status:** _____

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

Full Name of Inventor: Olivier Breyne

Resident Address: 5, rue Rosset, 69004, Lyon, FRANCE

Post Office Address: same

Citizenship: France

DATE: _____

Olivier Breyne

Full Name of Inventor: You-Ping Chan

Resident Address: 14, Bd Jean XXIII, 69008 Lyon, FRANCE

Post Office Address: same

Citizenship: Maugrita

DATE: _____

You-Ping Chan

Full Name of Inventor: Patrick Jean

Resident Address: 21, rue Pere-Chevrier, 69007, Lyon, FRANCE

Post Office Address: same

Citizenship: France

DATE: _____

Patrick Jean

0970512110700